



Acoustic



Material Data Sheet

Acoustic performance



Acoustic characteristics (NRC)

	t [mm]	α [125 Hz]	α [250 Hz]	α [500 Hz]	α [1000 Hz]	α [2000 Hz]	α [4000 Hz]	NRC
WAVE HEX	25-70	0.1	0.4	0.6	0.5	0.5	0.5	0.53
KITE	40-75	0.15	0.3	0.6	0.6	0.6	0.6	0.53
FIELDS	45	0.1	0.3	0.5	0.4	0.4	0.6	0.40
PLAIN	40	0.1	0.3	0.5	0.4	0.4	0.4	0.40
ASPEN / FORESTA	65	0.11	0.31	0.48	0.34	0.42	0.46	0.39

Measurements according to ISO 354 - Reverberation Room Measurement Method, with no distance between panels and floor. Aspen panels were measured with Foresta system setup, involving 13.5 sqm, with and without backing, with sealed wooden beams covering the full perimeter of the system. For specific info, please consult Foresta Technical Datasheet.

Physical appearance & performance

Product type	Wall / ceiling panels for interior design	Fire Reaction UNI EN 13501-2	B-s2-d0
Color	Any NCS color from Mogu Acoustic palette or custom color	UV resistance UNI EN 15187	Excellent [grey: 5/5; blue scale: >6]
Odor	none with finishing; medium smell with natural touch	Dimensional variation UNI EN 1604	< 0.4% (40°C; RH=70%) -2.0% (70°C; RH=90%)
Density	100 kg/m ³	Thermal Conductivity UNI EN12664-2	0.050 W/mK (34 mm thickness)
Flexural Strength	0.05 MPa	TVOC emission rate ($\mu\text{g}/\text{m}^2\text{h}$)*	15
Compression Strength UNI EN 826	10.72 kPa	VVOC emission rate ($\mu\text{g}/\text{m}^2\text{h}$)*	none determined
Impact Resistance ISO 4211-4	10-200mm: no damage [5/5]; 400 mm: slight sign [4/5]	SVOC emission rate ($\mu\text{g}/\text{m}^2\text{h}$)*	none determined
Deformation	2.5% before rupture	*Results for VOC emissions based on 28-days chamber testing. Official results according to Indoor Air Comfort test by Eurofins.	

Declaration of Performance can be downloaded on www.mogu.bio/download/dop-A001

Mogu was founded on the belief that it is possible to employ Nature's intelligence to radically disrupt the design of everyday products, seeking a finer balance between the man-made and the rhythms of the natural ecosystem.

Mogu products are obtained by growing mycelium, the vegetative part of mushrooms, on organic fibres (low-value residues from agro-industrial value chains).

The products are the result of five years of continuous and iterative R&D on mycelium technology, guided by a strong product-driven approach.

